

JUNGFRAU

BRUSHED & CHOPPED

JUNGFRAU

OAK
NATURAL
BRUSHED & CHOPPED



DESIGN PANEL

3-LAYER

LENGTH (M): ACCORDING TO AVAILABILITY, UPON REQUEST

DIMENSIONS (mm)		PACKAGING (Pieces)
THICKNESS	WIDTH	PACKAGE SIZE
19	2030	25

TOP LAYER	Oak Thickness 8.1 mm
MIDDLE LAYER	Spruce Natural Thickness 6.8 mm
RÜCKLAGE	Spruce Natural Thickness 8.1 mm Non-Visible (Closed)
TOP LAMELLA WIDTH	Falling widths
MOISTURE CONTENT	KD 7% ± 2 Ex Works
EMISSION CLASS	E1, Formaldehyde value according to ÖNORM EN 13986 Formaldehyde content ≤ 0.01 ppm
BONDING	Melamine - Urea System Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)
DENSITY	approx. 770 kg/m ³
APPLICATION	Interior Use according to CE Certification, Type 4
QUALITY	<ul style="list-style-type: none">• Visible side / non-visible side• Slight cracks permitted; end cracks max. board width• Healthy, firmly intergrown knots permitted; knot splits and cracks are filled with anthracite-colored repair material.• Light boxwood permitted; dynamic impressions permitted• Wood-specific discolorations are desired
INFO	<p>The following properties must be observed:</p> <ul style="list-style-type: none">• Three-layer solid wood panels are made of solid wood• Swelling and shrinkage behavior must be considered• If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping• If the ambient humidity is too dry, slight warping or fine surface cracks may occur• These are natural wood characteristics and not production defects