

# PIZ BERNINA

BANDSAW CUT

## PIZ BERNINA

DOMESTIC LARCH  
NATURAL  
BANDSAW CUT



### DESIGN PANEL

3-LAYERED

LENGTH (M): 3.96 / 4.96

DIMENSIONS (mm)		PACKAGING (Pieces)
THICKNESS	WIDTH	PACKAGE SIZE
19	2030	20

#### QUALITY

- Visible Side / Non-Visible Side
- Crack- and gap-free
- Healthy, firmly attached knots allowed
- Filling/repairing knot tears and cracks allowed
- Light burls allowed
- 10% of the panel may be patched and repaired
- Discoloration and fungal infestation not allowed
- No knot accumulation

#### TOP LAYER

Larch | Thickness 7.1 mm

#### MIDDLE LAYER

Larch Natural | Thickness 6.8 mm

#### BOTTOM LAYER

Larch | Thickness 7.1 mm | Non-Visible (Closed)

#### TOP LAMELLA WIDTH

subject to availability

#### MOISTURE CONTENT

KD 8% ± 2 | Ex Works

#### EMISSION CLASS

E1, Formaldehyde value according to ÖNORM EN 13986  
Formaldehyde content ≤ 0.01 ppm

#### BONDING

Melamine - Urea System  
Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)

#### DENSITY

approx. 600 kg/m<sup>3</sup>, approx. 13.8 kg/m<sup>2</sup>

#### APPLICATION

Interior Use according to CE Certification, Type 4

#### INFO

- The following properties must be observed:
- Three-layer solid wood panels are made of solid wood
  - Swelling and shrinkage behavior must be considered
  - If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping
  - If the ambient humidity is too dry, slight warping or fine surface cracks may occur
  - These are natural wood characteristics and not production defects