# EIGER

OAK
STEAMED
SANDED

## ALPINE WALL PANEL

3-LAYER, 4-SIDE PROFILED

LENGTH (M): 1.8 - 3.0 RANDOM

| DIMENSIONS (mm) | | |
|---|---|---|
| THICKNESS | WIDTH | |
| | Tongue Measurement | Covering Dimension |
| 19 +/-1 | 93 | 85 |
| 19 +/-1 | 113 | 105 |
| 19 +/-1 | 133 | 125 |
| 19 +/-1 | 153 | 145 |
| 19 +/-1 | 173 | 165 |
| 19 +/-1 | 193 | 185 |
| 19 +/-1 | 213 | 205 |
| 19 +/-1 | 223 | 215 |

| | |
|---|---|
| TOP LAYER | Oak, Medium Grade, Steamed \| Thickness 9.0 mm |
| MIDDLE LAYER | Spruce Natural \| Thickness 6.8 mm |
| BOTTOM LAYER | Spruce Natural \| Thickness 6.8 mm \| Non-Visible |
| APPLICATION | Interior Use according to CE Certification, Type 4 |
| QUALITY | • Healthy, firmly attached knots allowed<br>• Knot tears and cracks are filled/repaired with anthracite-colored filler<br>• Light burls allowed<br>• Dynamic imprints allowed<br>• Wood-specific discoloration desired |
| INFO | The following properties must be observed:<br>• Three-layer solid wood planks are made of solid wood<br>• Swelling and shrinkage behavior must be considered<br>• If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping<br>• If the ambient humidity is too dry, slight warping or fine surface cracks may occur<br>• These are natural wood characteristics and not production defects |