

JUNGFRAU

OAK NATURAL BRUSHED



DESIGN PANEL

3-LAYER

DIMENSIONS (mm)

THICKNESS

LENGTH (M): ACCORDING TO AVAILABILITY, UPON REQUEST

WIDTH

20	1220 / 2000	25
TOP LAYER	Oak Thickness 5.0 mm	
MIDDLE LAYER	Spruce Natural Thickness 10.0 mm	
RÜCKLAGE	Spruce Natural Thickness 5.0 mm Non-Visible (Closed)	
TOP LAMELLA WIDTH	Falling widths	
MOISTURE CONTENT	KD 7% ± 2 Ex Works	
EMISSION CLASS	E1, Formaldehyde value according to ÖNORM EN 13986 Formaldehyde content ≤ 0.01 ppm	
BONDING	Melamine - Urea System Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)	
DENSITY	approx. 770 kg/m³	
APPLICATION	Interior Use according to CE Certification, Type 4	
QUALITY	 Visible side / non-visible side Slight cracks permitted; end cracks max. board width Healthy, firmly intergrown knots permitted; knot splits and cracks are filled with anthracite-colored repair material. Light boxwood permitted; dynamic impressions permitted Wood-specific discolorations are desired 	
INFO	The following properties must be observed: Three-layer solid wood panels are made of solid wood Swelling and shrinkage behavior must be considered If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping If the ambient humidity is too dry, slight warping or fine surface cracks may	

PACKAGING (Pieces)

PACKAGE SIZE

SPRING 2025 WWW.MAREINER.COM

• These are natural wood characteristics and not production defects