



JUNGFRAU

CHOPPED

JUNGFRAU

OAK
NATURAL
CHOPPED



DESIGN PANEL

3-LAYER

LENGTH (M): ACCORDING TO AVAILABILITY, UPON REQUEST

DIMENSIONS (mm)		PACKAGING (Pieces)
THICKNESS	WIDTH	PACKAGE SIZE
23	1220 / 2000	25

TOP LAYER	Oak Thickness 8.1 mm
MIDDLE LAYER	Spruce Natural Thickness 6.8 mm
RÜCKLAGE	Spruce Natural Thickness 8.1 mm Non-Visible (Closed)
TOP LAMELLA WIDTH	Falling widths
MOISTURE CONTENT	KD 7% ± 2 Ex Works
EMISSION CLASS	E1, Formaldehyde value according to ÖNORM EN 13986 Formaldehyde content ≤ 0.01 ppm
BONDING	Melamine - Urea System Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)
DENSITY	approx. 770 kg/m³
APPLICATION	Interior Use according to CE Certification, Type 4
QUALITY	• Visible side / non-visible side • Slight cracks permitted; end cracks max. board width • Healthy, firmly intergrown knots permitted; knot splits and cracks are filled with anthracite-colored repair material. • Light boxwood permitted; dynamic impressions permitted • Wood-specific discolorations are desired
INFO	The following properties must be observed: • Three-layer solid wood panels are made of solid wood • Swelling and shrinkage behavior must be considered • If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping • If the ambient humidity is too dry, slight warping or fine surface cracks may occur • These are natural wood characteristics and not production defects