## MARMOLADA SANDED

0

63

10

\*

See.

(D)

## MARMOLADA

SPRUCE CHARACTER Steamed Sanded



## **DESIGN PANEL**

3-LAYER

LENGTH (M): 3,96

DIMENSIONS (mm)		PACKAGING (Pieces)
THICKNESS	WIDTH	PACKAGE SIZE
20	1220 / 2000	20
QUALITY	<ul> <li>Visible Side / Non-Visible Side</li> <li>Crack- and gap-free</li> <li>Healthy, firmly attached knots allowed</li> <li>Filling/repairing knot tears and cracks allowed</li> <li>Light burls allowed</li> <li>10% of the panel may be patched and repaired</li> <li>Discoloration and fungal infestation not allowed</li> <li>No knot accumulation</li> </ul>	
TOP LAYER	Spruce Steamed   Thickness 5.0 mm	
MIDDLE LAYER	Spruce Natural   Thickness 10.0 mm	
BOTTOM LAYER	Spruce Steamed   Thickness 5.0 mm   Non-Visible (Closed)	
TOP LAMELLA WIDTH	137 mm	
MOISTURE CONTENT	KD 8% ± 2   Ex Works	
EMISSION CLASS	E1, Formaldehyde value according to ÖNORM EN 13986 Formaldehyde content ≤ 0.01 ppm	
BONDING	Melamine - Urea System Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)	
DENSITY	approx. 450 kg/m³, approx. 9.0 kg/m²	
APPLICATION	Interior Use according to CE Certification, Type 4	
INFO	<ul> <li>The following properties must be observed:</li> <li>Three-layer solid wood panels are made of solid wood</li> <li>Swelling and shrinkage behavior must be considered</li> <li>If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping</li> <li>If the ambient humidity is too dry, slight warping or fine surface cracks may occur</li> <li>These are natural wood characteristics and not production defects</li> </ul>	