

The image shows a close-up of a wood surface with a bandsaw cut pattern. The wood grain is visible, showing concentric growth rings and some knots. The bandsaw cut creates a series of parallel, slightly wavy lines across the wood. The text "PIZ NAIR" is printed in large, bold, white capital letters, and "BANDSAW CUT" is printed in smaller, white capital letters below it.

PIZ NAIR

BANDSAW CUT

PIZ NAIR

DOMESTIC LARCH
THERMALLY TREATED AT 212°
BANDSAW CUT



DESIGN PANEL

3-LAYERED

LENGTH (M): 3,96

DIMENSIONS (mm)		PACKAGING (Pieces)
THICKNESS	WIDTH	PACKAGE SIZE
21	1220 / 2000	20

QUALITY	<ul style="list-style-type: none">• Visible Side / Non-Visible Side• Crack- and gap-free• Healthy, firmly attached knots allowed• Filling/repairing knot tears and cracks allowed• Light burls allowed• 10% of the panel may be patched and repaired• Discoloration and fungal infestation not allowed• No knot accumulation
TOP LAYER	Larch Thermo Thickness 7.1 mm
MIDDLE LAYER	Larch Natural Thickness 6.8 mm
BOTTOM LAYER	Larch Thermo Thickness 7.1 mm Non-Visible (Closed)
TOP LAMELLA WIDTH	137 mm
MOISTURE CONTENT	KD 8% ± 2 Ex Works
EMISSION CLASS	E1, Formaldehyde value according to ÖNORM EN 13986 Formaldehyde content ≤ 0.01 ppm
BONDING	Melamine - Urea System Bonding: According to EN 13354 SWP/3 (boil-resistant bonding)
DENSITY	approx. 600 kg/m³, approx. 12.6 kg/m²
APPLICATION	Interior Use according to CE Certification, Type 4
INFO	<p>The following properties must be observed:</p> <ul style="list-style-type: none">• Three-layer solid wood panels are made of solid wood• Swelling and shrinkage behavior must be considered• If the ambient humidity is too high, the wood absorbs moisture, leading to dimensional changes and warping• If the ambient humidity is too dry, slight warping or fine surface cracks may occur• These are natural wood characteristics and not production defects